

# COMPARAZIONE DUREZZE

## HARDNESS COMPARISON TABLE

## COMPARAISON DE DURETÉ

HV Vickers Durezza <i>Hardness - Dureté</i>	HRC Rockwell Durezza <i>Hardness - Dureté</i>	HB Brinell Durezza <i>Hardness - Dureté</i>	Resistenza	
			<i>Tensile Strength - Résistance</i> N/mm <sup>2</sup>	Tons/sq. in.
940	68			
900	67			
864	66			
829	65			
800	64			
773	63			
745	62			
720	61			
698	60			
675	59			
655	58		2200	142
650		618	2180	141
640		608	2145	139
639	57	607	2140	138
630		599	2105	136
620		589	2070	134
615	56	584	2050	133
610		580	2030	131
600		570	1995	129
596	55	567	1980	128
590		561	1955	126
580		551	1920	124
578	54	549	1910	124
570		542	1880	122
560	53	532	1845	119
550		523	1810	117
544	52	517	1790	116
540		513	1775	115
530		504	1740	113
527	51	501	1730	112
520		494	1700	110
514	50	488	1680	109
510		485	1665	108
500		475	1630	105
497	49	472	1620	105
490		466	1595	103
484	48	460	1570	102
480		456	1555	101
473	47	449	1530	99
470		447	1520	98
460		437	1485	96
458	46	435	1480	96
450		428	1455	94
446	45	424	1440	93
440		418	1420	92

HV Vickers Durezza <i>Hardness - Dureté</i>	HRC Rockwell Durezza <i>Hardness - Dureté</i>	HB Brinell Durezza <i>Hardness - Dureté</i>	Resistenza	
			<i>Tensile Strength - Résistance</i> N/mm <sup>2</sup>	Tons/sq. in.
434	44	416	1400	91
423	43	402	1360	88
413	42	393	1330	86
403	41	383	1300	84
392	40	372	1260	82
382	39	363	1230	80
373	38	354	1200	78
364	37	346	1170	76
355	36	337	1140	74
350		333	1125	73
345	35	328	1110	72
340		323	1095	71
336	34	319	1080	70
330		314	1060	69
327	33	311	1050	68
320		304	1030	67
317	32	301	1020	66
310	31	295	995	64
302	30	287	970	63
300		285	965	62
295		280	950	61
293	29	278	940	61
290		276	930	60
287	28	273	920	60
285		271	915	59
280	27	266	900	58
275		261	880	57
272	26	258	870	56
270		257	865	56
268	25	255	860	56
265		252	850	55
260	24	247	835	54
255	23	242	820	53
250	22	238	800	52
245		233	785	51
243	21	231	780	50
240		228	770	50
235		223	755	49
230		219	740	48
225		214	720	47
220		209	705	46
215		204	690	45
210		199	675	44
205		195	660	43
200		190	640	41

Secondo norma ISO 18265:2003 per gli acciai (ad esclusione degli acciai rapidi)

According to ISO 18265:2003 for steels (except high speed steels) - Selon la norme ISO 18265:2003 pour les aciers (sauf les aciers rapides)